

High performance, completely maintenance-free, low self-discharge

100% precise quality testing, stable quality and high reliable performance

- Unique grid alloy formula and updated manufacturing technique
- Floating & standby use:up to 8 years
- Cycle use 1: Up to 260 cycles at 100% DOD
- Cycle use 2: Up to 500 cycles at 50% DOD

Application:

- *Telecommunications
- *Uninterruptable Power Supply
- *Electric Power System (EPS)
- *Emergency backup power supply

Construction:

ComponentRaw material PositiveLead dioxide NegativeLead

ContainerABS CoverABS


- *Alarm and security system
- *Communication power supply
- *DC power supply
- *Auto control system


SealantEpoxy Safety ValveRubber TerminalCopper SeparatorFiber glass ElectrolyteSulfuric acid




M8 Bolt

B5 Terminal










Battery Model	YD 12-65							
Designed Floating Life	Up to 8 years @20-25°C ambient temperature							
Capacity (25°C)	20HR(3.48A, 10.8V)	10HR(6.74A ,10.8V)	5HR(13.49A ,10.5V)	1HR(46.08A, 10.5V)				
capacity (23 c)	69.60 AH	67.40 AH	67.45 AH	46.08 AH				
Dimensions	Lenght	Width	Height	Total Height				
	350 mm	167 mm	174 mm	174 mm				
Approx Weight	21 Kg ± %3							
Internal Resistance	Full charged @25°C, equal or less than 8 mOhm							
Self Discharge	%2 capacity declined per month @25°C							
Capacity Affected By Temperature (20 HR)	40°C	25°C	0°C	-15°C				
	%102	%100	%85	%65				
Charge Voltage (25°C)	Cycle	e Use	Float Use					
	14.4-15.0V (-30 m V/°	C), max. Current:21.0 A	13.50 - 13.80 V (-20 m V/°C)					




















		Const	ant Cur	rent Di	scharg	e(CC,U	nit:A)	at 25°	C (77 °F))		
F.V/Time	5Min	10Min	15Min	30Min	1Hr	2Hr	3Hr	4Hr	5Hr	6Hr	10Hr	20Hr
1.85V/Cell	216.34	148.06	118.56	77.44	44.38	23.82	19.66	15.02	12.99	10.38	6.61	3.42
1.80V/Cell	220.47	150.89	120.83	78.92	45.23	24.27	20.03	15.31	13.24	10.57	6.74	3.48
1.75V/Cell	224.60	153.72	123.09	80.40	46.08	24.73	20.41	15.59	13.49	10.77	6.87	3.55
1.70V/Cell	244.82	162.94	130.48	83.60	46.89	25.16	20.77	15.87	13.73	10.96	6.99	3.61
1.67V/Cell	269.52	176.77	141.56	88.28	47.39	25.43	20.99	16.04	13.87	11.08	7.06	3.65
Constant Power Discharge (CP,Unit:W) at 25℃(77°F)												
F.V/Time	5Min	10Min	15Min	30Min	1Hr	2Hr	3Hr	4Hr	5Hr	6Hr	10Hr	20Hr
1.85V/Cell	421.86	288.71	231.20	151.00	86.55	46.45	38.33	29.29	25.33	20.23	12.90	6.67
1.80V/Cell	429.92	294.23	235.61	153.89	88.20	47.33	39.07	29.85	25.82	20.62	13.14	6.80
1.75V/Cell	437.98	299.74	240.03	156.77	89.85	48.22	39.80	30.41	26.30	21.00	13.39	6.92
1.70V/Cell	477.40	317.73	254.43	163.03	91.44	49.07	40.50	30.94	26.76	21.37	13.63	7.04
1.67V/Cell	525.57	344.71	276.04	172.14	92.41	49.59	40.93	31.27	27.05	21.60	13.77	7.12